

# IMPEX COLOR s.r.l.

## PRODUCT DATA SHEET

# MARMORINO POLVERE FINE

### CHARACTERISTICS AND UTILIZATIONS

The **Marmorino Polvere Fine** is a mixture of particular and selectioned dusts and marble grits with other mineral ingredients with prevalence lime and other different additives which facilitate and guarantee an excellent anchorage to the support.

The **Marmorino Polvere Fine** can be used both inside and outside: for its particular mineral composition, the **Marmorino Polvere Fine** has a good resistance both to the humidity and to the moulds. It has an excellent perspiration, even if it has a sufficient waterproofness.

### PREPARATION OF THE PRODUCT

Mix the **Marmorino Polvere Fine** with about 35% of water, using a low speed mixer; let the mixture rest for 20 minutes at least.

### APPLICATION

After treating carefully the bottoms, see technical data sheet "preparation of the bottoms", apply a first coat of material with a steel float, and paying attention to spread uniformly and plane the product, without blurs, lines, surmounts etc. After about 12 hours (according to the absorption and the environmental temperature), apply a second coat of **Marmorino Polvere Fine** with the same previous proceeding, and before it begins to get dry, polish with the steelfloat making progressively more and more pressure.

Further advice: during the summer season or with very absorbing plasters you should wet the walls before the application of the first and also the second coat to avoid the lines of the float, during the application of the first coat.

Protect, in case of outside works, the wall for three days at least (particularly during the periods of high humidity).

The **Marmorino Polvere Fine** has natural colours, it is the type of marble which gives a tone. The **Marmorino Polvere Fine** can be treated with transparent silossanic protection coat (Silatop Coat) to improve the water repellence.

### THECNICAL DATA

Yield	: 1 - 1,5 Kg/mq.
Packets	: Kg 15 each
Specific Weight	: 1,1 about at 20 °C.
Exsiccation	: 2 hours to the touch, 24 hours in depth.